

Technical Data Sheet



Tankguard Special Primer and Mid coat

Product description

This is a two component polyamine cured novolac epoxy coating. It has very good chemical resistance. Can be used as primer or mid coat in atmospheric and immersed environments. Suitable for properly prepared carbon steel, galvanised steel and stainless steel substrates.

Typical use

Marine:

Designed as a part of an internal tank coating system for chemical tanks. This coating has very good resistance to a wide range of products. Refer to Marine Product Resistance List on www.jotunprl.com.

Colours

light red (primer), yellow (mid coat)

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	63 ± 2 %
Gloss level (60 °)	ISO 2813	matt (0-35)
Flash point	ISO 3679 Method 1	25 °C
VOC-Solvent Emission Directive	SED (1999/13/EC)	189 g/kg

The provided data is typical for factory produced products, subject to slight variation depending on colour.

All data is valid for mixed paint.

Gloss level: According to Jotun Performance Coatings' definition.

Recommended film thickness per coat

Film thickness and spreading rate	Dry film thickness (µm)	Wet film thickness (µm)	Theoretical spreading rate (m ² /l)
Minimum	80	125	7,9
Maximum	150	240	4,2
Typical	100	160	6,3

Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

Technical Data Sheet

Tankguard Special Primer and Mid coat



Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	Sa 2½ (ISO 8501-1)	Sa 2½ (ISO 8501-1)
Coated surfaces	Clean, dry and undamaged compatible coating (ISO 12944-4 6.1)	Clean, dry and undamaged compatible coating (ISO 12944-4 6.1)
Stainless steel	The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads to impart a scratch pattern to the surface and to remove all polish from the surface.	Abrasive blast cleaning to achieve a surface profile using approved non-metallic abrasive media which is suitable to achieve a sharp and angular surface profile.
Galvanised steel	The surface shall be clean, dry and appear with a rough and dull profile.	Light brush blasting using non-metallic abrasive leaving a clean, rough and even pattern.

Application

Application methods

The product can be applied by

- Spray: Use airless spray.
- Brush: Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.

Product mixing ratio (by volume)

If Tankguard Special Primer Comp A, mix with Tankguard Special Comp B.
If Tankguard Special Mid Coat Comp A, mix with Tankguard Special Comp B.

Tankguard Special Primer Comp A	4	part(s)
Tankguard Special Mid Coat Comp A	4	part(s)
Tankguard Special Comp B	1	part(s)

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 23

Guiding data for airless spray

Nozzle tip (inch/1000):	17-21
Pressure at nozzle (minimum):	150 bar/2100 psi

Technical Data Sheet

Tankguard Special Primer and Mid coat



Drying and Curing time

Substrate temperature	10 °C	15 °C	23 °C	40 °C
Surface (touch) dry	18 h	10 h	5.5 h	2 h
Dried to over coat, minimum	52 h	36 h	20 h	10 h
Dried to over coat, maximum, atmospheric	18 d	12 d	7 d	4 d
Dried/cured for service		14 d	7 d	3 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85%, and within the DFT range of the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness. Dry sand sprinkled on the surface can be brushed off without sticking to or causing damage to the surface.

Dried to over coat, minimum: The shortest time allowed before the next coat can be applied.

Dried to over coat, maximum, atmospheric: The longest time allowed before the next coat can be applied without any surface preparation.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature	23 °C
Induction time	20 min
Pot life	3 h

Reduced at higher temperatures

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	140 °C	140 °C
Immersed, sea water	70 °C	90 °C

Further resistance information can be found in Marine Product Resistance List and/or in Protective Product Resistance List available on Jotun's website, or contact your local Jotun office.

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

Technical Data Sheet

Tankguard Special Primer and Mid coat



Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: novolac epoxy

Subsequent coat: novolac epoxy

For touch up, stripe coating and minor repair work, Tankguard TU can be used.

Packaging (typical)

	Volume (litres)	Size of containers (litres)
Tankguard Special Primer Comp A	16	20
Tankguard Special Mid Coat Comp A	16	20
Tankguard Special Comp B	4	5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Tankguard Special Primer Comp A	24 month(s)
Tankguard Special Mid Coat Comp A	24 month(s)
Tankguard Special Comp B	24 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Technical Data Sheet

Tankguard Special Primer and Mid coat



Colour variation

Products primarily meant for use as primers and antifoulings may have slight color variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
