



## Steelmaster Approved Topcoats

The following list of Jotun topcoats are approved for use with Steelmaster products. These topcoats have been tested by Jotun for compatibility, adhesion and fire tested prior to approval for use with Steelmaster products.

### Approved Topcoats – Jotun

Jotun Product	Steelmaster 60WB	Steelmaster 1200WF	Steelmaster 60SB	Steelmaster 120SB	Steelmaster 60/120
Conseal Touch-Up	Yes	Yes	Yes	Yes	Yes
Hardtop CA	Yes*	Yes*	Yes*	Yes*	Yes*
Hardtop XP	No	Yes	Yes	Yes	Yes
Hardtop XPL	Yes	Yes	Yes	Yes	Yes
Hardtop AX	Yes	Yes	Yes	Yes	Yes
Pioner Topcoat	Yes	Yes	Yes	Yes	Yes
Futura AS	Yes*	Yes*	Yes*	Yes*	Yes*
Pilot WF	No	No	Yes	Yes	Yes
Hardtop HB	Yes	Yes	Yes	Yes	Yes
Pilot ACR	No	No	Yes	Yes	Yes
Hardtop Eco	No	Yes	No	Yes	No
Hardtop Pro	No	Yes	No	No	No
Hardtop Optima	No	No	Yes*	Yes*	Yes*

### Notes

- Hardtop CA - Yes\*** - There is a possibility of discoloration of the first coat of Hardtop CA when applied on Steelmaster products. It is recommended to first apply a thin coat of 30-40 microns, allow to dry, then apply a full coat of Hardtop CA at 60 microns dft.
- Hardtop Optima - Yes\*** - There is a possibility of discoloration of the first coat of Hardtop Optima when applied on Steelmaster SB products. It is recommended to apply a thin coat of 30-40 microns, allow to dry, then apply a full coat of Hardtop Optima at 60 microns dft.
- Futura AS - Yes\*** - Approved subject to application of two coats of Futura AS to a total minimum dft of 80 microns (2x40microns)
- The maximum total dft of the topcoat should not exceed 125 microns
- Prior to application of the topcoat ensure the Steelmaster system is fully dry to recoat and the Steelmaster system has been applied at the specified dft.
- The Steelmaster surface must be clean, dry and free from contamination before applying the top coat
- Jotun does not accept responsibility for top coats manufactured by third parties. Jotun does not have control over consistency or quality of products manufactured by other parties.
- Please also refer to the Steelmaster application guide
- We reserve the right to update and modify this document as required

Document identification:	TSS/ SM-02	Prepared by	N Shrikumar
Date:	03.03.2016	Approved by	
Version:	8	Number of pages	2



### **Important Information**

The information in this guideline is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this guideline without first obtaining written confirmation from Jotun as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this guideline or otherwise) is correct to the best of our knowledge. However, we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless specifically agreed in writing to do so, Jotun does not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage, direct or indirect, arising out of the use of the product. We hereby disclaim any warranties or representations, expressed or implied, by operation of law or otherwise, including without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical information given is subject to our Conditions of Sale, which can be provided to you by your local Jotun supplier. The information contained in this guideline is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local Jotun representative that this guideline is current prior to using the product.

Document identification:	TSS/ SM-02	Prepared by	N Shrikumar
Date:	03.03.2016	Approved by	
Version:	8	Number of pages	2