

Jotun Shopprimers

PRODUCT	Muki PVB	Muki EPS	Muki AC	Muki Z 2001	Muki Z 3000	Muki Z WB-14FW
Generic type	PVB	Epoxy	Acrylic	Low zinc silicate	Medium zinc silicate	Medium zinc silicate
Volume solids %	13	25	40	28	28	62
VOC g/l	710	610	57	660	600	0
Protection time – months	3–5	3–5	3–5	6–8	8–10	12–14
Recommended DFT on smooth plate – µm	20–30	15–50	20–30	15–20	15–20	15–25
Colours	Red	Red Grey	Red Grey	Green Red Grey	Green Red Grey	Grey
Weldability	Fair	Good	Good	Excellent	Good	Optimum
Cutability	Excellent	Excellent	Excellent	Excellent	Good	Optimum

Jotun A/S
 P.O. Box 2021,
 N-3248 Sandefjord, Norway
 Tel:+47 33 45 70 00
 jotun.com

